


DIRECTA ceramir[®] | Ceramir CAD/CAM BLOCKS Step by Step Guide


Preparation of the restoration



1
Remove the restoration from the attachment with a diamond bur




2
Final polish with goat hair brush and cotton / linen buffs



3
Prepare restoration
1. Apply a very thin layer of edelweiss VENEER BOND to inner surface, rub surface for 30 sec
2. Dry surface with air
3. Light cure for 20 sec
(Or apply equivalent bonding/primer and use it according to manufacturer's instructions.)

Preparation of the tooth



4
Clean the tooth with polishing paste free from oil and fluoride



5
Apply 37% phosphoric acid (Enamel 15-30 sec/ Dentin 15 sec)

Preparation of the tooth




6
Rinse with water and gently dry the surface



7
Prepare tooth
1. Apply dentin bonding (Rub surface with dentin bonding for 20 sec.)
2. Light cure (according to manufacturer's IFU)

Seating of the restoration



8
Cementation
1. Apply adhesive resin cement/ composite into restoration and seat restoration
2. Light cure (according to manufacturer's IFU)



9
Remove excess cement